

Technical Data Sheet

Schuladur A GF 10 HI2 BLK968001

Polybutylene Terephthalate
LyondellBasell Industries
Engineering Plastics

Product Description

10% glass fibre reinforced PBT compound

General

- | | |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 10% Filler by Weight |
| Processing Method | • Injection Molding |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.37 g/cm ³	1.37 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/2.16 Kg)	30 cm ³ /10min	30 cm ³ /10min	ISO 1133
Water Absorption			ISO 62
Equilibrium, 73°F (23°C), 50% Rh	0.30 %	0.30 %	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	653000 psi	4500 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	13100 psi	90.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.5 %	3.5 %	ISO 527-2/1A/5
Flexural Modulus ¹	551000 psi	3800 MPa	ISO 178
Flexural Stress ¹ (4.6% Strain)	17700 psi	122 MPa	ISO 178

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	1.9 ft·lb/in ²	4.0 kJ/m ²	
73°F (23°C)	2.4 ft·lb/in ²	5.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	17 ft·lb/in ²	35 kJ/m ²	
73°F (23°C)	17 ft·lb/in ²	35 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	419 °F	215 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	365 °F	185 °C	ISO 75-2/af
Vicat Softening Temperature			
--	401 °F	205 °C	ISO 306/B50
--	424 °F	218 °C	ISO 306/A50

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	IEC 60093
Volume Resistivity	1.0E+13 ohms·m	1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	300 V	300 V	IEC 60112

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	1.9 in/min	49 mm/min	ISO 3795
0.0787 In (2.00 Mm)	1.9 in/min	49 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

Schuladur A GF 10 HI2 BLK968001

Polybutylene Terephthalate
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	248 °F	120 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	482 to 500 °F	250 to 260 °C
Mold Temperature	158 to 194 °F	70 to 90 °C

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.