

Technical Data Sheet

Schuladur A NV 12 SHI

Polybutylene Terephthalate
LyondellBasell Industries
Engineering Plastics

Product Description

Low viscosity non-reinforced PBT compound providing high impact strength

General

Features	• Good Flow	• Impact Modified
Processing Method	• Injection Molding	
Resin ID (ISO 1043)	• PBT	

Physical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.25 g/cm ³	1.25 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°c/2.16 Kg)	25 cm ³ /10min	25 cm ³ /10min	ISO 1133
Water Absorption			ISO 62
Equilibrium, 73°f (23°c), 50% Rh	0.40 %	0.40 %	

Mechanical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	290000 psi	2000 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	6820 psi	47.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	5.0 %	5.0 %	ISO 527-2/1A/50

Impact

	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°f (-30°c)	3.8 ft·lb/in ²	8.0 kJ/m ²	
73°f (23°c)	7.1 ft·lb/in ²	15 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°f (-30°c)	No Break	No Break	
73°f (23°c)	No Break	No Break	

Thermal

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	280 °F	138 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	126 °F	52.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	320 °F	160 °C	ISO 306/B50
--	421 °F	216 °C	ISO 306/A50

Electrical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	600 V	600 V	IEC 60112

Flammability

	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1200 °F	650 °C	
0.12 In (3.0 Mm)	1200 °F	650 °C	

Technical Data Sheet



Schuladur A NV 12 SHI

Polybutylene Terephthalate
LyondellBasell Industries
Engineering Plastics


Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

Schuldur A NV 12 SHI

Polybutylene Terephthalate
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 °F	100 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.05 %	0.05 %
Processing (Melt) Temp	464 to 482 °F	240 to 250 °C
Mold Temperature	158 to 194 °F	70 to 90 °C

Notes

These are typical property values not to be construed as specification limits.