



Technical Data Sheet

SCHULADUR[®] E-12672

Polybutylene Terephthalate
Engineering Plastics

Product Description

PBT

General

Processing Method • Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.19	1.19 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	7540 psi	52.0 MPa	ASTM D638

Notes

¹ 2.0 in/min (50 mm/min)

Notes

These are typical property values not to be construed as specification limits.