

## Technical Data Sheet

**Schuladur A GF20 BLK968094**

Polybutylene Terephthalate

**Product Description**

20% glass fibre reinforced PBT compound

**Processing Method** Injection Molding  
**Filler/Reinforcement** Glass Fiber, 20%  
**Resin ID** PBT-GF

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Volume Flow Rate, (250 °C/2.16 kg)	20	cm <sup>3</sup> /10 min	ISO 1133
Density, (Method A)	1.45	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Strain at Break, (Type 1A, 5 mm/min)	2.5	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 5 mm/min)	115	MPa	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	7000	MPa	ISO 527-1
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	8.0	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	57	kJ/m <sup>2</sup>	ISO 179
<b>Hardness</b>			
Ball Indentation Hardness, (H 961/30)	205	MPa	ISO 2039-1
Ball Pressure Test, (200 °C)	Pass		IEC 60695-10-2
<b>Thermal</b>			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	208	°C	ISO 306
(A (10N), 50 °C/h)	218	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	215	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	195	°C	ISO 75-2/A
<b>Electrical</b>			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	400	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
<b>Flammable</b>			

<b>Burning Rate</b>			
(2.00 mm)	40	mm/min	ISO 3795
(2.00 mm)	40	mm/min	FMVSS 302
<b>Glow Wire Flammability Index</b>			
(1.5 mm)	650	°C	IEC 60695-2-12
(3.0 mm)	650	°C	IEC 60695-2-12
<b>Additional Information</b>			
Water Absorption 23C/50RH	0.3	%	ISO 62
<b>UL Information</b>			
<b>Flammability Classification</b>			
(1.5 mm)	HB		IEC 60695-11-10, -20
(3.0 mm)	HB		IEC 60695-11-10, -20
		<b>Nominal Value</b>	<b>Units</b>
<b>Injection Parameters</b>			
Drying Time	2.0 to 4.0	hr	
Drying Temperature	120	°C	
Suggested Max Moisture	0.05	%	
Processing (Melt) Temp	250 to 260	°C	
Mold Temperature	70 to 90	°C	