

Technical Data Sheet

Schuladur A3 GF30 FR1 GRY967685



Polybutylene Terephthalate + ASA

Product Description

High flow 30% glass fiber reinforced flame retardant halogenated PBT/ASA compound surface quality and low warpage; halogenated.

| | |
|-----------------------------|---|
| Processing Method | Injection Molding |
| Attribute | Filled; Good Dimensional Stability; Good Surface Finish; Halogenated; Low Warpage |
| Additive | Flame Retardant |
| Filler/Reinforcement | Glass Fiber, 30% |
| Resin ID | PBT/ASA GF30 FR(17) (ISO 1043) |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---------------|-------------------------|----------------|
| Physical | | | |
| Melt Volume Flow Rate, (260 °C/5.0 kg) | 27 | cm ³ /10 min | ISO 1133 |
| Density, (Method A) | 1.58 | g/cm ³ | ISO 1183 |
| Mechanical | | | |
| Tensile Strain at Break, (Type 1A, 5 mm/min) | 1.5 | % | ISO 527-2 |
| Tensile Stress at Break, (Type 1A, 5 mm/min) | 115 | MPa | ISO 527-2 |
| Tensile Modulus, (1 mm/min, Type 1A) | 11000 | MPa | ISO 527-1 |
| Impact | | | |
| Charpy Impact Strength - Notched | | | |
| (23 °C, Type 1, Edgewise, Notch A) | 6.5 | kJ/m ² | ISO 179 |
| (-30 °C, Type 1, Edgewise, Notch A) | 6.0 | kJ/m ² | ISO 179 |
| Charpy Impact Strength - Unnotched | | | |
| (23 °C, Type 1, Edgewise) | 40 | kJ/m ² | ISO 179 |
| (-30 °C, Type 1, Edgewise) | 48 | kJ/m ² | ISO 179 |
| Hardness | | | |
| Ball Pressure Test, (175 °C) | Pass | | IEC 60695-10-2 |
| Thermal | | | |
| Vicat Softening Temperature | | | |
| (B (50N), 50 °C/h) | 152 | °C | ISO 306 |
| (A (10N), 50 °C/h) | 213 | °C | ISO 306 |
| Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise) | 210 | °C | ISO 75-2/B |
| Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise) | 181 | °C | ISO 75-2/A |

| | | | |
|----------------------------------|----------|--------|----------------------|
| RTI Elec | | | |
| (1.5 mm) | 75.0 | °C | UL 746B |
| (3.0 mm) | 75.0 | °C | UL 746B |
| (0.75 mm) | 75.0 | °C | UL 746B |
| RTI Imp | | | |
| (1.5 mm) | 75.0 | °C | UL 746B |
| (3.0 mm) | 75.0 | °C | UL 746B |
| (0.75 mm) | 75.0 | °C | UL 746B |
| RTI Str | | | |
| (1.5 mm) | 75.0 | °C | UL 746B |
| (3.0 mm) | 75.0 | °C | UL 746B |
| (0.75 mm) | 75.0 | °C | UL 746B |
| Electrical | | | |
| Volume Resistivity | >1.0E+13 | ohm*m | IEC 62631-3-1 |
| Comparative Tracking Index (CTI) | 250 | V | IEC 60112 |
| Surface Resistivity | >1.0E+15 | ohm | IEC 60093 |
| Flammable | | | |
| Burning Rate | | | |
| (2.00 mm, Self-Extinguishing) | 0.0 | mm/min | ISO 3795 |
| (2.00 mm, Self-Extinguishing) | 0.0 | mm/min | FMVSS 302 |
| Glow Wire Flammability Index | | | |
| (0.75 mm) | 960 | °C | IEC 60695-2-12 |
| (1.5 mm) | 960 | °C | IEC 60695-2-12 |
| (3.0 mm) | 960 | °C | IEC 60695-2-12 |
| Glow Wire Ignition Temperature | | | |
| (0.75 mm) | 675 | °C | IEC 60695-2-13 |
| (1.5 mm) | 675 | °C | IEC 60695-2-13 |
| (3.0 mm) | 675 | °C | IEC 60695-2-13 |
| Oxygen Index | 30 | % | ISO 4589-2 |
| UL Information | | | |
| Flame Rating | | | |
| (1.5 mm) | V-0 | | UL 94 |
| (3.0 mm) | V-0 | | UL 94 |
| (0.75 mm) | V-0 | | UL 94 |
| Flammability Classification | | | |
| (0.75 mm) | V-0 | | IEC 60695-11-10, -20 |
| (1.5 mm) | V-0 | | IEC 60695-11-10, -20 |
| (3.0 mm) | V-0 | | IEC 60695-11-10, -20 |
| UL File Number | E86615 | | |

| Injection Parameters | Nominal Value | Units |
|-----------------------------|----------------------|--------------|
| Drying Time | 2.0 to 4.0 | hr |
| Drying Temperature | 120 | °C |
| Suggested Max Moisture | 0.04 | % |
| Screw Speed | <250 | mm/sec |
| Processing (Melt) Temp | 250 to 260 | °C |
| Injection Rate | Slow- Moderate | |
| Back Pressure | 2.00 to 8.00 | MPa |
| Mold Temperature | 60 to 90 | °C |