

## Technical Data Sheet

### Schuladur A1 GF15 K1947BLK968094



Polybutylene Terephthalate + PET

#### Product Description

15% glass fibre reinforced PBT/PET blend.

**Processing Method** Injection Molding

**Filler/Reinforcement** Glass Fiber, 15%

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Volume Flow Rate, (260 °C/2.16 kg)	19	cm <sup>3</sup> /10 min	ISO 1133
Density, (Method A)	1.43	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Strain at Break, (Type 1A, 5 mm/min)	2.4	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 5 mm/min)	112	MPa	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	6700	MPa	ISO 527-1
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	5.0	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	27	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise)	18	kJ/m <sup>2</sup>	ISO 179
<b>Thermal</b>			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	194	°C	ISO 306
(A (10N), 120 °C/h)	215	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	213	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	186	°C	ISO 75-2/A
<b>Electrical</b>			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Surface Resistivity	>1.0E+15	ohm	IEC 60093
<b>Injection Parameters</b>			
Drying Time	4.0 to 6.0	hr	
Drying Temperature	120	°C	
Suggested Max Moisture	0.02	%	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	80 to 110	°C	