

Technical Data Sheet

Accutech POL051G40L

Polycarbonate
LyondellBasell Industries
Engineering Plastics

General

- Filler / Reinforcement • Glass Fiber, 40% Filler by Weight
- Forms • Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.50	1.50 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	841000 psi	5800 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	20600 psi	142 MPa	
Break	20500 psi	141 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	5.0 %	5.0 %	
Flexural Modulus	1.60E+6 psi	11000 MPa	ASTM D790
Flexural Strength	31300 psi	216 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	3.4 ft·lb/in	180 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	114	114	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	291 °F	144 °C	
264 Psi (1.8 Mpa), Unannealed	284 °F	140 °C	

Additional Information

Ash Content, ASTM D2584: 40%

Notes

These are typical property values not to be construed as specification limits.