

**Technical Data Sheet**

***Diamond* PC-1410RIM GY7415GRY**



Polycarbonate

**Product Description**

Injection/Extrusion Grade PolycarbonateMedium Flow - Clear and Colors AvailableAdd "R" for Added ReleaseAdd "U" for UV StabilizerMeets GMP.PC.018R

**Processing Method** Extrusion; Injection Molding  
**Attribute** Medium Flow  
**Appearance** Clear/Transparent; Colors Available

<b>Typical Properties</b>	<b>Nominal Value</b>	<b>Units</b>	<b>Test Method</b>
<b>Physical</b>			
Melt Flow Rate	10	g/10 min	ASTM D1238
Density - Specific Gravity	1.21	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>			
Tensile Strength at Yield	62.1	MPa	ASTM D638
Flexural Modulus	2280	MPa	ASTM D790
Tensile Elongation at Break	>130	%	ASTM D638
Flexural Strength	98.6	MPa	ASTM D790
<b>Impact</b>			
Notched Izod Impact, (23 °C, 3.18 mm)	750	J/m	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load Unannealed (264 psi)	132	°C	ASTM D648