

Technical Data Sheet

Matrixx 50N5006

Polycarbonate
LyondellBasell Industries
Engineering Plastics

General

Forms • Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.20	1.20 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	9000 psi	62.1 MPa	ASTM D638
Flexural Modulus	340000 psi	2340 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	13 ft·lb/in	690 J/m	ASTM D256
Gardner Impact	> 320 in·lb	> 36.2 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	265 °F	129 °C	
264 Psi (1.8 Mpa), Unannealed	260 °F	127 °C	
RTI Str	200 °F	93.3 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94

Notes

These are typical property values not to be construed as specification limits.