

Technical Data Sheet

# Matrixx 52N5006

Polycarbonate  
LyondellBasell Industries  
Engineering Plastics

General	
Additive	• Flame Retardant
Features	• Flame Retardant
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.22	1.22 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	10 g/10 min	10 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	9000 psi	62.1 MPa	ASTM D638
Flexural Modulus	340000 psi	2340 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	13 ft·lb/in	690 J/m	ASTM D256
Gardner Impact	> 320 in·lb	> 36.2 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	265 °F	129 °C	
264 Psi (1.8 Mpa), Unannealed	260 °F	127 °C	
RTI Str	200 °F	93.3 °C	UL 746B

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 In (1.5 Mm)	V-2	V-2	
0.12 In (3.0 Mm)	V-0	V-0	

**Notes**

These are typical property values not to be construed as specification limits.