

Technical Data Sheet

# Matrixx 54N5006

Polycarbonate  
LyondellBasell Industries  
Engineering Plastics

General	
Additive	• Flame Retardant
Features	• Flame Retardant
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.23	1.23 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	10 g/10 min	10 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	8800 psi	60.7 MPa	ASTM D638
Flexural Modulus	325000 psi	2240 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	13 ft·lb/in	690 J/m	ASTM D256
Gardner Impact	> 320 in·lb	> 36.2 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	265 °F	129 °C	
264 Psi (1.8 Mpa), Unannealed	260 °F	127 °C	
RTI Str	239 °F	115 °C	UL 746B

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-0	V-0	UL 94

Technical Data Sheet

# Matrixx 54N5006

Polycarbonate  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	4.0 hr	4.0 hr
Rear Temperature	480 to 570 °F	249 to 299 °C
Middle Temperature	480 to 570 °F	249 to 299 °C
Front Temperature	480 to 570 °F	249 to 299 °C
Processing (Melt) Temp	540 to 570 °F	282 to 299 °C
Mold Temperature	160 to 220 °F	71 to 104 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa
Screw Speed	40 to 75 rpm	40 to 75 rpm
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

**Injection Notes**  
-20°F Dewpoint

**Notes**

These are typical property values not to be construed as specification limits.