

Technical Data Sheet

# Perlex R2515

Polycarbonate  
LyondellBasell Industries  
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight		
Uses	• Electrical Housing	• Housings	
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.28 g/cm <sup>3</sup>	1.28 g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	9.0 g/10 min	9.0 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield)	11200 psi	77.0 MPa	ISO 527-2
Flexural Modulus	711000 psi	4900 MPa	ISO 178
Flexural Stress	21000 psi	145 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (Area) (73°F (23°C))	4.76 ft·lb/in <sup>2</sup>	10.0 kJ/m <sup>2</sup>	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	280 °F	138 °C	ISO 75-2/B
264 Psi (1.8 Mpa), Unannealed	270 °F	132 °C	ISO 75-2/A
Vicat Softening Temperature	293 °F	145 °C	ISO 306/B50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flame Rating	HB	HB	UL 94

**Notes**

These are typical property values not to be construed as specification limits.