

Technical Data Sheet

Polyflam PC 510GF

Polycarbonate
 LyondellBasell Industries
 Engineering Plastics

Product Description

Flame Retardent, 10% Glass Reinforced, Polycarbonate

General

- | | |
|-------------------|---------------------|
| Features | • Flame Retardant |
| Processing Method | • Injection Molding |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.27	1.27 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/2.16 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	7980 psi	55.0 MPa	ASTM D638
Flexural Modulus ²	450000 psi	3100 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.2 ft·lb/in	120 J/m	ASTM D256
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 In (1.5 Mm), All	V-0	V-0	
0.10 In (2.5 Mm), All	5VA	5VA	
0.13 In (3.4 Mm), All	5VA	5VA	

Technical Data Sheet

Polyflam PC 510GF

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Suggested Max Moisture	< 0.02 %	< 0.02 %
Rear Temperature	480 to 530 °F	249 to 277 °C
Middle Temperature	480 to 550 °F	249 to 288 °C
Front Temperature	480 to 550 °F	249 to 288 °C
Nozzle Temperature	480 to 550 °F	249 to 288 °C
Processing (Melt) Temp	480 to 550 °F	249 to 288 °C
Mold Temperature	160 to 220 °F	71 to 104 °C
Back Pressure	< 100 psi	< 0.689 MPa
Screw Speed	40 to 75 rpm	40 to 75 rpm

Notes

- ¹ 2.0 in/min (50 mm/min)
- ² 0.051 in/min (1.3 mm/min)

Notes

These are typical property values not to be construed as specification limits.