

## Technical Data Sheet

# Polyflam RPC 31XP GF10 FR

Polycarbonate  
LyondellBasell Industries  
Engineering Plastics

### Product Description

Flame retardant glass fiber reinforced PC; halogen free according to DIN VDE 0472 part 815

### General

Features	• Flame Retardant	• Halogen Free
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.27 g/cm <sup>3</sup>	1.27 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (260°C/5.0 Kg)	9.0 cm <sup>3</sup> /10min	9.0 cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	522000 psi	3600 MPa	ISO 527-1/1A/1
Tensile Stress			
Yield	10200 psi	70.0 MPa	ISO 527-2/1A/50
Break	9140 psi	63.0 MPa	ISO 527-2
Tensile Strain (Yield)	3.5 %	3.5 %	ISO 527-2/1A/50
Nominal Tensile Strain at Break	6.3 %	6.3 %	ISO 527-2
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	4.3 ft·lb/in <sup>2</sup>	9.0 kJ/m <sup>2</sup>	
73°F (23°C)	4.8 ft·lb/in <sup>2</sup>	10 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	29 ft·lb/in <sup>2</sup>	60 kJ/m <sup>2</sup>	
73°F (23°C)	24 ft·lb/in <sup>2</sup>	50 kJ/m <sup>2</sup>	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	282 °F	139 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	270 °F	132 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	223 °F	106 °C	ISO 306/B50
--	302 °F	150 °C	ISO 306/A50
Ball Pressure Test (275°F (135°C))	Pass	Pass	IEC 60695-10-2
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	FMVSS 302
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	ISO 3795
Flame Rating			UL 94
0.06 In (1.5 Mm)	V-1	V-1	
0.12 In (3.0 Mm)	V-0	V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.12 In (3.0 Mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1560 °F	850 °C	
0.12 In (3.0 Mm)	1560 °F	850 °C	

Technical Data Sheet

# Polyflam RPC 31XP GF10 FR

Polycarbonate  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 to 248 °F	100 to 120 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.02 %	0.02 %
Processing (Melt) Temp	500 to 518 °F	260 to 270 °C
Mold Temperature	122 to 176 °F	50 to 80 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	725 to 1450 psi	5.00 to 10.0 MPa
Screw Speed	< 591 in/min	< 15 m/min

**Notes**

These are typical property values not to be construed as specification limits.