

Technical Data Sheet

# POLYMAN<sup>®</sup> (PC) XP 01 RN / RS

Polycarbonate  
Engineering Plastics

**Product Description**  
high flow PC grade for parts with low wall thickness, RN: food contact grade - RS: UV-stabilized

General	
Features	• Good Flow
Uses	• Thin-walled Parts
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PC

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.20 g/cm <sup>3</sup>	1.20 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	29 cm <sup>3</sup> /10min	29 cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage	0.40 to 0.60 %	0.40 to 0.60 %	ISO 294-4

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	334000 psi	2300 MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	8990 psi	62.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	6.0 %	6.0 %	ISO 527-2/1A/50

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	29 ft·lb/in <sup>2</sup>	61 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	No Break	No Break	ISO 179/1eU

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	16000 psi	110 MPa	ISO 2039-1

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	279 °F	137 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	253 °F	123 °C	ISO 75-2/Af
Vicat Softening Temperature	300 °F	149 °C	ISO 306/B50

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	275 V	275 V	IEC 60112

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate 0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification 0.06 in (1.5 mm)	V-2	V-2	IEC 60695-11-10, -20
0.12 in (3.0 mm)	V-2	V-2	
Glow Wire Flammability Index 0.08 in (2.0 mm)	1560 °F	850 °C	IEC 60695-2-12

Technical Data Sheet

**POLYMAN<sup>®</sup> (PC) XP 01 RN / RS**

Polycarbonate  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	248 °F	120 °C
Drying Time	4.0 to 12 hr	4.0 to 12 hr
Processing (Melt) Temp	536 to 590 °F	280 to 310 °C
Mold Temperature	185 to 239 °F	85 to 115 °C

**Notes**

These are typical property values not to be construed as specification limits.