



Technical Data Sheet

Qr Resin QR-1000-GFR40

Polycarbonate
 LyondellBasell Industries
 Engineering Plastics

Product Description

Available with UV (V) or Release (R).
 Flame Packages Available (0.0625 in min. thickness): 94V-2, 94V-0, 94-5VA

General

Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Features	• Good Toughness
Appearance	• Colors Available • Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	1.53	1.53 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	10 to 20 g/10 min	10 to 20 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (Yield)	22500 psi	155 MPa	ASTM D638
Flexural Modulus	1.38E+6 psi	9510 MPa	ASTM D790
Flexural Strength (Yield)	26000 psi	179 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Unnotched Izod Impact (73°F (23°C))	20 ft·lb/in	1100 J/m	ASTM D4812
-------------------------------------	-------------	----------	------------

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	310 °F	154 °C	
264 Psi (1.8 Mpa), Unannealed	295 °F	146 °C	

Technical Data Sheet

Qr Resin QR-1000-GFR40

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	3.0 to 6.0 hr	3.0 to 6.0 hr
Drying Time, Maximum	6.0 hr	6.0 hr
Rear Temperature	560 to 600 °F	293 to 316 °C
Middle Temperature	580 to 620 °F	304 to 327 °C
Front Temperature	600 to 640 °F	316 to 338 °C
Nozzle Temperature	590 to 630 °F	310 to 332 °C
Processing (Melt) Temp	600 to 640 °F	316 to 338 °C
Mold Temperature	180 to 240 °F	82 to 116 °C

Notes

These are typical property values not to be construed as specification limits.