

Technical Data Sheet

Qr Resin QR-1018

Polycarbonate
LyondellBasell Industries
Engineering Plastics

Product Description
Available with UV (V) or Release (R).

General	
Features	<ul style="list-style-type: none"> High Impact Resistance
Automotive Specifications	<ul style="list-style-type: none"> CHRYSLER MS-DB-145 CPN1829 Color: Non-matched Color CHRYSLER MS-DB-145 CPN1829 Color: 112 Non-matched Color
Appearance	<ul style="list-style-type: none"> Colors Available <ul style="list-style-type: none"> Natural Color
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.20	1.20 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	18 g/10 min	18 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	8900 psi	61.4 MPa	ASTM D638
Flexural Modulus	340000 psi	2340 MPa	ASTM D790
Flexural Strength (Yield)	13000 psi	89.6 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	12 ft·lb/in	640 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	280 °F	138 °C	
264 Psi (1.8 Mpa), Unannealed	270 °F	132 °C	

Technical Data Sheet

Qr Resin QR-1018

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Drying Time, Maximum	4.0 hr	4.0 hr
Rear Temperature	500 to 540 °F	260 to 282 °C
Middle Temperature	520 to 560 °F	271 to 293 °C
Front Temperature	540 to 560 °F	282 to 293 °C
Nozzle Temperature	530 to 560 °F	277 to 293 °C
Processing (Melt) Temp	540 to 580 °F	282 to 304 °C
Mold Temperature	160 to 200 °F	71 to 93 °C

Notes

These are typical property values not to be construed as specification limits.