

Technical Data Sheet

# Lucent Pc PC/ABS-1208

Polycarbonate + ABS  
 LyondellBasell Industries  
 Engineering Plastics

**Product Description**

Polycarbonate + ABS, General Purpose Injection Grade

Colors Available  
 Add "R" for Added Release  
 Add "U" for UV Stabilized

**General**

Features	• General Purpose
Uses	• General Purpose
Appearance	• Colors Available
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 Kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	8000 psi	55.2 MPa	ASTM D638
Tensile Elongation (Break)	> 140 %	> 140 %	ASTM D638
Flexural Modulus	335000 psi	2310 MPa	ASTM D790
Flexural Strength	12200 psi	84.1 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 In (3.18 Mm))	12 ft·lb/in	640 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	225 °F	107 °C	ASTM D648

**Notes**

These are typical property values not to be construed as specification limits.