

Technical Data Sheet

RONFALIN[®] C C230FR G20

Polycarbonate + ABS
Engineering Plastics

General	
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant
Uses	• Electrical Parts

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.25 g/cm ³	1.25 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	17 g/10 min	17 g/10 min	ISO 1133
Molding Shrinkage	0.30 to 0.50 %	0.30 to 0.50 %	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	827000 psi	5700 MPa	ISO 527-2
Tensile Stress (Break)	10900 psi	75.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.5 %	2.5 %	ISO 527-2

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength	3.8 ft-lb/in ²	8.0 kJ/m ²	ISO 179

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	270 °F	132 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	248 °F	120 °C	ISO 75-2/A
Vicat Softening Temperature	275 °F	135 °C	ISO 306/A50
Ball Pressure Test (257°F (125°C))	Pass	Pass	IEC 60695-10-2

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 in (1.5 mm)	V-0	V-0	
0.13 in (3.2 mm)	V-0	V-0	

Notes

These are typical property values not to be construed as specification limits.