

## Technical Data Sheet

**Ronfalin C130 BUE 3-1368 L**

Polycarbonate + ABS

**Product Description**

Perloy C130 is a high impact strength easy flow PC/ABS alloy with excellent sub-zero ductility. Having a vicat temp. of 130°C applications include electronic and automotive.

**Regulatory Status**

For regulatory compliance information, see *Ronfalin C130 BUE 3-1368 L* [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

<b>Status</b>	Commercial: Active
<b>Availability</b>	Africa-Middle East; Asia-Pacific; Europe; Latin America; North America
<b>Forms</b>	Pellets
<b>Application</b>	Appliances; General Purpose

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (260 °C/5.0 kg)	15	g/10 min	ISO 1133
Density	1.15	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Stress at Yield	55	MPa	ISO 527-2
Tensile Strain at Break	>50	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527-1
Flexural Stress	80	MPa	ISO 178
<b>Impact</b>			
Notched Izod Impact (Area), (23 °C)	45.0	kJ/m <sup>2</sup>	ASTM D256
<b>Thermal</b>			
Vicat Softening Temperature, (B (50N), 50 °C/h)	130	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	125	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	108	°C	ISO 75-2/A
<b>UL Information</b>			
Flame Rating	HB		UL 94

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.