

Technical Data Sheet

Schulablend (PC/ABS) M/MB 6305 SF

Polycarbonate + ABS
LyondellBasell Industries
Engineering Plastics

Product Description

High flow and high heat resistant PC/ABS blend.

Available with or without UV stabilization. (Former name: SCHULABLEND® M/MB 6 SF K3013)

General

Features	• Good Flow	• High Heat Resistance
UL File Number	• E86615	
Processing Method	• Injection Molding	
Resin ID (ISO 1043)	• ABS+PC	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.16 g/cm ³	1.16 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (260°C/5.0 Kg)	27 cm ³ /10min	27 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	319000 psi	2200 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	7980 psi	55.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	6.0 %	6.0 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	26 ft·lb/in ²	55 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	14800 psi	102 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	275 °F	135 °C	ISO 306/B50
Ball Pressure Test (266°F (130°C))	Pass	Pass	IEC 60695-10-2
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	2.4 in/min	60 mm/min	ISO 3795
0.0787 In (2.00 Mm)	2.4 in/min	60 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.08 In (2.0 Mm)	1200 °F	650 °C	

Additional Information

The tradename "Schulablend" may be abbreviated "SBL" in documents or on labels.

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

Schulablend (PC/ABS) M/MB 6305 SF

Polycarbonate + ABS
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 to 230 °F	100 to 110 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	500 to 536 °F	260 to 280 °C
Mold Temperature	158 to 212 °F	70 to 100 °C

Notes

These are typical property values not to be construed as specification limits.