

Technical Data Sheet

# Icorene N7130

Polyethylene  
LyondellBasell Industries  
Custom Powders

## Product Description

ICORENE® N7130 is a polyethylene based coating powder designed for encapsulating wire goods. Compared with standard powders, this grade will have improved flow behaviour, process faster and enable users to make savings through thinner coatings achieved at lower oven temperatures.

This grade is used for fluidized bed coating applications by manual dip coating.

General			
Features	<ul style="list-style-type: none"> <li>Abrasion Resistant</li> </ul>	<ul style="list-style-type: none"> <li>Good Flow</li> </ul>	<ul style="list-style-type: none"> <li>Good Processing Stability</li> </ul>
Uses	<ul style="list-style-type: none"> <li>Coating Applications</li> <li>Decorative Railing</li> </ul>	<ul style="list-style-type: none"> <li>Industrial Applications</li> <li>Piping</li> </ul>	<ul style="list-style-type: none"> <li>Wire &amp; Cable Applications</li> </ul>
Appearance	<ul style="list-style-type: none"> <li>Unspecified Color</li> </ul>		
Forms	<ul style="list-style-type: none"> <li>Powder</li> </ul>		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.924 g/cm <sup>3</sup>	0.924 g/cm <sup>3</sup>	ASTM D1505
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	1160 psi	8.00 MPa	ASTM D638
Tensile Elongation (Break)	> 500 %	> 500 %	ASTM D638
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	49	49	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	-94.0 °F	-70.0 °C	ASTM D746
Peak Melting Temperature	244 °F	118 °C	ASTM D3418

## Notes

These are typical property values not to be construed as specification limits.