

Technical Data Sheet

Qr Resin QR-5000-GF30

Polyether Imide
 LyondellBasell Industries
 Engineering Plastics

General	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Chemical Resistant • High Stiffness • High Heat Resistance • High Strength
Appearance	• Colors Available • Natural Color
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.50	1.50 g/cm ³	ASTM D792

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	22500 psi	155 MPa	ASTM D638
Flexural Modulus	1.20E+6 psi	8270 MPa	ASTM D790
Flexural Strength (Yield)	30000 psi	207 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.5 ft·lb/in	80 J/m	ASTM D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	420 °F	216 °C	
264 Psi (1.8 Mpa), Unannealed	410 °F	210 °C	

Technical Data Sheet

Qr Resin QR-5000-GF30

Polyether Imide
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	300 °F	149 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Drying Time, Maximum	6.0 hr	6.0 hr
Rear Temperature	650 to 690 °F	343 to 366 °C
Middle Temperature	670 to 710 °F	354 to 377 °C
Front Temperature	690 to 730 °F	366 to 388 °C
Nozzle Temperature	680 to 720 °F	360 to 382 °C
Processing (Melt) Temp	690 to 730 °F	366 to 388 °C
Mold Temperature	275 to 325 °F	135 to 163 °C

Notes

These are typical property values not to be construed as specification limits.