



Technical Data Sheet

Qr Resin QR-5000

Polyether Imide
 LyondellBasell Industries
 Engineering Plastics

General			
Features	• Chemical Resistant	• Good Toughness	• High Heat Resistance
Appearance	• Colors Available	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.27	1.27 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 Kg)	10 g/10 min	10 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	15000 psi	103 MPa	ASTM D638
Flexural Modulus	460000 psi	3170 MPa	ASTM D790
Flexural Strength (Yield)	20000 psi	138 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.80 ft·lb/in	43 J/m	ASTM D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	402 °F	206 °C	
264 Psi (1.8 Mpa), Unannealed	380 °F	193 °C	

Technical Data Sheet

Qr Resin QR-5000

Polyether Imide
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	300 °F	149 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Drying Time, Maximum	6.0 hr	6.0 hr
Rear Temperature	610 to 650 °F	321 to 343 °C
Middle Temperature	620 to 670 °F	327 to 354 °C
Front Temperature	650 to 700 °F	343 to 371 °C
Nozzle Temperature	640 to 680 °F	338 to 360 °C
Processing (Melt) Temp	650 to 700 °F	343 to 371 °C
Mold Temperature	270 to 320 °F	132 to 160 °C

Notes

These are typical property values not to be construed as specification limits.