

Technical Data Sheet

Matrixx 80S7150

Polyethylene Terephthalate
LyondellBasell Industries
Engineering Plastics

General

- | | |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 15% Filler by Weight |
| Forms | • Pellets |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.44	1.44 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	14000 psi	96.5 MPa	ASTM D638
Flexural Modulus	725000 psi	5000 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.80 ft·lb/in	43 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	425 °F	218 °C	
264 Psi (1.8 Mpa), Unannealed	320 °F	160 °C	
RTI Elec	167 °F	75.0 °C	UL 746B
RTI Imp	167 °F	75.0 °C	UL 746B
RTI Str	167 °F	75.0 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94

Additional Information

The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with Matrixx test methods.

Notes

These are typical property values not to be construed as specification limits.