

Technical Data Sheet

# SCHULADUR<sup>®</sup> E GF 35

Polyethylene Terephthalate  
Engineering Plastics

**Product Description**  
35% glass fibre reinforced PET compound

General	
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.62 g/cm <sup>3</sup>	1.62 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (280°C/2.16 kg)	28 cm <sup>3</sup> /10min	28 cm <sup>3</sup> /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.89E+6 psi	13000 MPa	ISO 527-2/1A/1
Tensile Stress (Break)	23200 psi	160 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	1.7 %	1.7 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	2.9 ft·lb/in <sup>2</sup>	6.0 kJ/m <sup>2</sup>	
73°F (23°C)	3.3 ft·lb/in <sup>2</sup>	7.0 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	17 ft·lb/in <sup>2</sup>	35 kJ/m <sup>2</sup>	
73°F (23°C)	17 ft·lb/in <sup>2</sup>	35 kJ/m <sup>2</sup>	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	473 °F	245 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	437 °F	225 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	482 °F	250 °C	ISO 306/A50
--	455 °F	235 °C	ISO 306/B50
Ball Pressure Test (428°F (220°C))	Pass	Pass	IEC 60695-10-2

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	200 V	200 V	IEC 60112

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	0.87 in/min	22 mm/min	ISO 3795
0.0787 in (2.00 mm)	0.87 in/min	22 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.08 in (2.0 mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.08 in (2.0 mm)	1380 °F	750 °C	

**Additional Information**  
 1.) Not for use in food contact applications  
 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

**SCHULADUR<sup>®</sup> E GF 35**

Polyethylene Terephthalate  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	248 °F	120 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.02 %	0.02 %
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	536 to 554 °F	280 to 290 °C
Mold Temperature	176 to 230 °F	80 to 110 °C

**Notes**

These are typical property values not to be construed as specification limits.