

Technical Data Sheet

# Schulaketon GF 15

Polyketone, Aliphatic  
LyondellBasell Industries  
Engineering Plastics

**Product Description**

15% glass fiber reinforced aliphatic Polyketon

**General**

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PK

**Physical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.34 g/cm <sup>3</sup>	1.34 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (240°C/2.16 Kg)	6.0 cm <sup>3</sup> /10min	6.0 cm <sup>3</sup> /10min	ISO 1133

**Mechanical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	653000 psi	4500 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	12300 psi	85.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	4.0 %	4.0 %	ISO 527-2/1A/5

**Impact**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°F (-40°C)	2.4 ft·lb/in <sup>2</sup>	5.0 kJ/m <sup>2</sup>	
73°F (23°C)	4.8 ft·lb/in <sup>2</sup>	10 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			
-40°F (-40°C)	24 ft·lb/in <sup>2</sup>	50 kJ/m <sup>2</sup>	ISO 179
73°F (23°C)	29 ft·lb/in <sup>2</sup>	60 kJ/m <sup>2</sup>	ISO 179/1eU

**Thermal**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	421 °F	216 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	403 °F	206 °C	ISO 75-2/af
Vicat Softening Temperature			
--	406 °F	208 °C	ISO 306/B50
--	430 °F	221 °C	ISO 306/A50

**Electrical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112

**Flammability**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1290 °F	700 °C	
0.12 In (3.0 Mm)	1290 °F	700 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1340 °F	725 °C	
0.12 In (3.0 Mm)	1340 °F	725 °C	

Technical Data Sheet

# Schulaketon GF 15

Polyketone, Aliphatic  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.15 %	0.15 %
Processing (Melt) Temp	473 to 500 °F	245 to 260 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

### Injection Notes

Before start, nozzle, screw, barrel and hot-runner have to be cleaned with Polyolefin. Contamination of other material leads to degradation or crosslinking of SCHULAKETON®.

Avoid shut down for more than 15 minutes at moulding temperature, because of degradation and crosslinking of SCHULAKETON®. Purge with Polyolefin!

### Notes

These are typical property values not to be construed as specification limits.