

Technical Data Sheet

# Schulaketon GF 30 4DE ORANGE

Polyketone, Aliphatic  
LyondellBasell Industries  
Engineering Plastics

**Product Description**

30% glass fiber reinforced aliphatic Polyketone, flame-retardant, halogen free. Available in orange colour.

**General**

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Flame Retardant • Halogen Free
UL File Number	• E86615
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PK GF30 FR(40)

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density	1.45 g/cm <sup>3</sup>	1.45 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (240°C/5.0 Kg)	17 cm <sup>3</sup> /10min	17 cm <sup>3</sup> /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Modulus	1.16E+6 psi	8000 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	18900 psi	130 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.5 %	3.5 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Charpy Notched Impact Strength (73°F (23°C))	6.2 ft·lb/in <sup>2</sup>	13 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	26 ft·lb/in <sup>2</sup>	55 kJ/m <sup>2</sup>	ISO 179/1eU

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	408 °F	209 °C	ISO 75-2/ Af
RTI Elec			UL 746B
0.016 In (0.40 Mm)	122 °F	50.0 °C	
0.024 In (0.60 Mm)	122 °F	50.0 °C	
0.031 In (0.8 Mm)	122 °F	50.0 °C	
0.06 In (1.6 Mm)	122 °F	50.0 °C	
0.12 In (3.0 Mm)	122 °F	50.0 °C	
RTI Imp			UL 746B
0.016 In (0.40 Mm)	122 °F	50.0 °C	
0.024 In (0.60 Mm)	122 °F	50.0 °C	
0.031 In (0.8 Mm)	122 °F	50.0 °C	
0.06 In (1.6 Mm)	122 °F	50.0 °C	
0.12 In (3.0 Mm)	122 °F	50.0 °C	
RTI Str			UL 746B
0.016 In (0.40 Mm)	122 °F	50.0 °C	
0.024 In (0.60 Mm)	122 °F	50.0 °C	
0.031 In (0.8 Mm)	122 °F	50.0 °C	
0.06 In (1.6 Mm)	122 °F	50.0 °C	
0.12 In (3.0 Mm)	122 °F	50.0 °C	

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Electric Strength 73°F (23°C), 0.0394 In (1.00 Mm), In Air	970 V/mil	38 kV/mm	IEC 60243-1

Technical Data Sheet

# Schulaketon GF 30 4DE ORANGE

Polyketone, Aliphatic  
 LyondellBasell Industries  
 Engineering Plastics

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Comparative Tracking Index	600 V	600 V	IEC 60112
High Amp Arc Ignition (HAI)			UL 746A
0.016 In (0.40 Mm)	PLC 0	PLC 0	
0.024 In (0.60 Mm)	PLC 0	PLC 0	
0.03 In (0.8 Mm)	PLC 0	PLC 0	
0.06 In (1.6 Mm)	PLC 0	PLC 0	
0.12 In (3.0 Mm)	PLC 0	PLC 0	
Hot-wire Ignition (HWI)			UL 746A
0.016 In (0.40 Mm)	PLC 0	PLC 0	
0.024 In (0.60 Mm)	PLC 0	PLC 0	
0.03 In (0.8 Mm)	PLC 0	PLC 0	
0.06 In (1.6 Mm)	PLC 0	PLC 0	
0.12 In (3.0 Mm)	PLC 0	PLC 0	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	ISO 3795
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	FMVSS 302
Flame Rating			
0.016 In (0.40 Mm)	V-0	V-0	UL 94 IEC 60695-11-10, -20
0.024 In (0.60 Mm)	V-0	V-0	UL 94 IEC 60695-11-10, -20
0.031 In (0.8 Mm)	V-0	V-0	UL 94
0.06 In (1.6 Mm)	• V-0 • 5VA	• V-0 • 5VA	UL 94 IEC 60695-11-10, -20
0.12 In (3.0 Mm)	• V-0 • 5VA	• V-0 • 5VA	UL 94 IEC 60695-11-10, -20
0.03 In (0.8 Mm)	V-0	V-0	IEC 60695-11-10, -20
Glow Wire Flammability Index			IEC 60695-2-12
0.024 In (0.60 Mm)	1760 °F	960 °C	
0.031 In (0.8 Mm)	1760 °F	960 °C	
0.06 In (1.6 Mm)	1760 °F	960 °C	
0.12 In (3.0 Mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.024 In (0.60 Mm)	1520 °F	825 °C	
0.031 In (0.8 Mm)	1520 °F	825 °C	
0.06 In (1.6 Mm)	1560 °F	850 °C	
0.12 In (3.0 Mm)	1520 °F	825 °C	

Technical Data Sheet

# Schulaketon GF 30 4DE ORANGE

Polyketone, Aliphatic  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.15 %	0.15 %
Processing (Melt) Temp	446 to 482 °F	230 to 250 °C
Mold Temperature	140 to 212 °F	60 to 100 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

## Injection Notes

Before start, nozzle, screw, barrel and hot-runner have to be cleaned with Polyolefin. Contamination of other material leads to degradation or crosslinking of SCHULAKETON®.

Avoid shut down for more than 8 minutes at moulding temperature, because of degradation and crosslinking of SCHULAKETON®. Purge with Polyolefin!

Mould surfaces in contact with melt are recommended to be of non-corrosive steel, chrome content >12%

## Notes

These are typical property values not to be construed as specification limits.