

Technical Data Sheet

# SCHULAKETON GF 30 FC

Polyketone, Aliphatic  
Engineering Plastics

**Product Description**  
30% glass fiber reinforced aliphatic Polyketone for food contact applications

General	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PK GF30

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.47 g/cm <sup>3</sup>	1.47 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (240°C/2.16 kg)	10 cm <sup>3</sup> /10min	10 cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.4 %	1.4 %	
Flow	0.80 %	0.80 %	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.09E+6 psi	7500 MPa	ISO 527-2/1A/1
Tensile Stress (Break)	18900 psi	130 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0 %	3.0 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			
-22°F (-30°C)	4.8 ft·lb/in <sup>2</sup>	10 kJ/m <sup>2</sup>	ISO 179/1eA
73°F (23°C)	7.1 ft·lb/in <sup>2</sup>	15 kJ/m <sup>2</sup>	ISO 179/1e
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	29 ft·lb/in <sup>2</sup>	60 kJ/m <sup>2</sup>	
73°F (23°C)	31 ft·lb/in <sup>2</sup>	65 kJ/m <sup>2</sup>	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/Af
264 psi (1.8 MPa), Unannealed, 0.157 in (4.00 mm)	419 °F	215 °C	
Vicat Softening Temperature			
--	419 °F	215 °C	ISO 306/A50
--	401 °F	205 °C	ISO 306/B50

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	IEC 60093
Volume Resistivity	1.0E+13 ohms·m	1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112

Technical Data Sheet

# SCHULAKETON GF 30 FC

Polyketone, Aliphatic  
Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in (1.5 mm)	1290 °F	700 °C	
0.12 in (3.0 mm)	1290 °F	700 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in (1.5 mm)	1340 °F	725 °C	
0.12 in (3.0 mm)	1340 °F	725 °C	

Technical Data Sheet

# SCHULAKETON GF 30 FC

Polyketone, Aliphatic  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.15 %	0.15 %
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	473 to 500 °F	245 to 260 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

### Injection Notes

Before start, nozzle, screw, barrel and hot-runner have to be cleaned with Polyolefin. Contamination of other material leads to degradation or crosslinking of SCHULAKETON®.

Avoid shut down for more than 15 minutes at moulding temperature, because of degradation and crosslinking of SCHULAKETON®. Purge with Polyolefin!

### Notes

These are typical property values not to be construed as specification limits.