



Technical Data Sheet

# POLYTROPE<sup>®</sup> TPP 1026E

Thermoplastic Polyolefin Elastomer  
Engineering Plastics

**Product Description**

Extrusion TPO 13% Talc

**General**

- |                        |                              |
|------------------------|------------------------------|
| Filler / Reinforcement | • Talc, 13% Filler by Weight |
| Processing Method      | • Extrusion                  |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density / Specific Gravity	1.00	1.00 g/cm <sup>3</sup>	ASTM D792
----------------------------	------	------------------------	-----------

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength <sup>1</sup> (Yield)	4060 psi	28.0 MPa	ASTM D638
Flexural Modulus <sup>2</sup>	290000 psi	2000 MPa	ASTM D790

Additional Information	Nominal Value (English)	Nominal Value (SI)	Test Method
------------------------	-------------------------	--------------------	-------------

Filler Content	13 %	13 %	ASTM D5630
----------------	------	------	------------

**Notes**

<sup>1</sup> 2.0 in/min (50 mm/min)

<sup>2</sup> 0.051 in/min (1.3 mm/min)

**Notes**

These are typical property values not to be construed as specification limits.