

Technical Data Sheet

# POLYTROPE<sup>®</sup> TPP 293

Thermoplastic Polyolefin Elastomer  
Engineering Plastics

**Product Description**

TPO 3% Glass Fiber

**General**

- |                        |                                      |
|------------------------|--------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 3.0% Filler by Weight |
| Processing Method      | • Injection Molding                  |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.942	0.940 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow <sup>1</sup>	9.5E-3 in/in	0.95 %	Internal Method

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength <sup>2</sup> (Yield)	3650 psi	25.2 MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	680 %	680 %	ASTM D638
Flexural Modulus <sup>3</sup>	105000 psi	724 MPa	ASTM D790

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	59	59	ASTM D2240

Additional Information	Nominal Value (English)	Nominal Value (SI)	Test Method
Filler Content	5.0 %	5.0 %	ASTM D5630

**Notes**

- <sup>1</sup> 5x7 in plaque
- <sup>2</sup> 2.0 in/min (50 mm/min)
- <sup>3</sup> 0.051 in/min (1.3 mm/min)

**Notes**

These are typical property values not to be construed as specification limits.