

Technical Data Sheet

***Polytrope* TPP 1817UVP-2599 GRYGRY**



Thermoplastic Polyolefin Elastomer

Product Description

TPO High Flow 17% Talc

Processing Method Injection Molding

Attribute High Flow

Filler/Reinforcement Talc, 17%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density - Specific Gravity	1.02	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield, (50 mm/min)	17.0	MPa	ASTM D638
Flexural Modulus, (1.3 mm/min)	1650	MPa	ASTM D790
Additional Information			
Filler Content	19	%	ASTM D5630