

Technical Data Sheet

Polytrope TPP 508UV-2A057 CNCH GRY



Thermoplastic Polyolefin Elastomer

Product Description

Polytrope TPP 508U is an Unfilled, UV Stabilized Polypropylene

Processing Method Injection Molding

Attribute UV Stabilized

Appearance Colors Available

Application General Purpose

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate	13	g/10 min	ASTM D1238
Density - Specific Gravity	0.888	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield	16.2	MPa	ASTM D638
Tensile Modulus	55.5	MPa	ASTM D638
Hardness			
Rockwell Hardness	95		ASTM D785
Thermal			
Deflection Temperature Under Load Unannealed (66 psi)	91	°C	ASTM D648