

Technical Data Sheet

SCHULAFORM[®] 9 A GF 10

Acetal (POM) Copolymer
Engineering Plastics

Product Description

10% glass fibre reinforced POM

General

- | | |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 10% Filler by Weight |
| Processing Method | • Injection Molding |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density	1.48 g/cm ³	1.48 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	7.00 cm ³ /10min	7.00 cm ³ /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Modulus	725000 psi	5000 MPa	ISO 527-2/1A/1
Tensile Stress (Break)	12300 psi	85.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0 %	3.0 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Charpy Notched Impact Strength			ISO 179/1A
-22°F (-30°C)	1.9 ft·lb/in ²	4.0 kJ/m ²	
73°F (23°C)	1.9 ft·lb/in ²	4.0 kJ/m ²	
Charpy Unnotched Impact Strength			
-22°F (-30°C)	17 ft·lb/in ²	35 kJ/m ²	ISO 179/1U
73°F (23°C)	17 ft·lb/in ²	35 kJ/m ²	ISO 179/1eU

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Ball Indentation Hardness (H 358/30)	26000 psi	179 MPa	ISO 2039-1
--------------------------------------	-----------	---------	------------

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Heat Deflection Temperature			ISO 75-2/ Af
264 psi (1.8 MPa), Unannealed	316 °F	158 °C	
Vicat Softening Temperature	304 °F	151 °C	ISO 306/B50

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (CTI)	600 V	600 V	UL 746

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
--------------	-------------------------	--------------------	-------------

Burning Rate			
0.0787 in (2.00 mm)	1.3 in/min	34 mm/min	ISO 3795
0.0787 in (2.00 mm)	1.3 in/min	34 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
--	1160 °F	625 °C	
0.12 in (3.0 mm)	1160 °F	625 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
--	1200 °F	650 °C	
0.12 in (3.0 mm)	1200 °F	650 °C	

Technical Data Sheet

SCHULAFORM[®] 9 A GF 10

Acetal (POM) Copolymer
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 °F	100 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	374 to 428 °F	190 to 220 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

Notes

These are typical property values not to be construed as specification limits.