

Technical Data Sheet

# Ecolent GPP

Polypropylene  
 LyondellBasell Industries  
 Engineering Plastics

**Product Description**

Glass Fiber Reinforced Polypropylene

Recycled Content  
 Add "U" for UV Stabilized  
 Add "H" for Heat Stabilized

**General**

- Filler / Reinforcement                      • Glass Fiber
- Recycled Content                              • Yes

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.10	1.10 g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	9200 psi	63.4 MPa	ASTM D638
Tensile Elongation (Break)	4.0 %	4.0 %	ASTM D638
Flexural Modulus	620000 psi	4270 MPa	ASTM D790
Flexural Strength	10500 psi	72.4 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 In (3.18 Mm))	2.2 ft·lb/in	120 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	225 °F	107 °C	ASTM D648

**Notes**

These are typical property values not to be construed as specification limits.