



Technical Data Sheet

Ferrex GPP-0215U

Polypropylene
 LyondellBasell Industries
 Engineering Plastics

Product Description

GPP-0215U is a 15% Glass-Reinforced, UV Stabilized Polypropylene

General

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Impact Modifier
Features	• UV Stabilized
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	12 g/10 min	12 g/10 min	ASTM D1238
---	-------------	-------------	------------

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Strength (73°F (23°C))	7700 psi	53.1 MPa	ASTM D638
--------------------------------	----------	----------	-----------

Flexural Modulus	453000 psi	3120 MPa	ASTM D790
------------------	------------	----------	-----------

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Notched Izod Impact (73°F (23°C))	1.4 ft-lb/in	75 J/m	ASTM D256
-----------------------------------	--------------	--------	-----------

Technical Data Sheet

Ferrex GPP-0215U

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	200 °F	93 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Rear Temperature	390 to 400 °F	199 to 204 °C
Middle Temperature	400 to 410 °F	204 to 210 °C
Front Temperature	410 to 420 °F	210 to 216 °C
Nozzle Temperature	420 to 430 °F	216 to 221 °C
Mold Temperature	115 to 140 °F	46 to 60 °C
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Screw Speed	100 to 150 rpm	100 to 150 rpm
Clamp Tonnage	2.0 to 3.0 tons/in ²	2.8 to 4.1 kN/cm ²
Screw L/D Ratio	20.0:1.0	20.0:1.0
Screw Compression Ratio	2.0:1.0	2.0:1.0

Notes

These are typical property values not to be construed as specification limits.