



## Technical Data Sheet

# ***Ferro Pp* HPP30GR45BK**

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

### Product Description

Please contact A. Schulman for additional information.

### General

Uses	<ul style="list-style-type: none"><li>• Automotive Applications</li></ul>
Forms	<ul style="list-style-type: none"><li>• Pellets</li></ul>
Processing Method	<ul style="list-style-type: none"><li>• Injection Molding</li></ul>

Technical Data Sheet

**Ferro Pp HPP30GR45BK**

Polypropylene  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

**Notes**

These are typical property values not to be construed as specification limits.