

Technical Data Sheet

# Ferro Pp LPP20BN62HB

Polypropylene  
 LyondellBasell Industries  
 Engineering Plastics

**Product Description**

LPP20BN62HB is a 20% Calcium Carbonate-Filled Polypropylene

**General**

Filler / Reinforcement	• Calcium Carbonate, 20% Filler by Weight
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	17 g/10 min	17 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	3790 psi	26.1 MPa	ASTM D638
Flexural Modulus - Tangent (73°F (23°C))	263000 psi	1810 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.4 ft·lb/in	75 J/m	ASTM D256
Gardner Impact (73°F (23°C))	192 in·lb	21.7 J	ASTM D5420

Technical Data Sheet

# Ferro Pp LPP20BN62HB

Polypropylene  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

**Notes**

These are typical property values not to be construed as specification limits.