

Technical Data Sheet

# Ferro Pp LPP60BC67NA

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

**General**

Filler / Reinforcement	• Calcium Carbonate, 60% Filler by Weight
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

**Physical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.57	1.57 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°c/2.16 Kg)	10 g/10 min	10 g/10 min	ASTM D1238

**Mechanical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	2600 psi	17.9 MPa	ASTM D638
Flexural Modulus	450000 psi	3100 MPa	ASTM D790
Flexural Strength (Yield)	5000 psi	34.5 MPa	ASTM D790

**Impact**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Gardner Impact	85.0 in-lb	9.60 J	ASTM D3029

Technical Data Sheet

**Ferro Pp LPP60BC67NA**

Polypropylene  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Rear Temperature	395 to 400 °F	202 to 204 °C
Middle Temperature	400 to 410 °F	204 to 210 °C
Front Temperature	410 to 415 °F	210 to 213 °C
Nozzle Temperature	415 to 425 °F	213 to 218 °C
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa

**Notes**

These are typical property values not to be construed as specification limits.