

Technical Data Sheet

# Ferro Pp NPP00NP01NA

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

**General**

Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

**Physical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.900	0.898 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238

**Mechanical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	2300 psi	15.9 MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	9.0 %	9.0 %	
Break	330 %	330 %	
Flexural Modulus	55000 psi	379 MPa	ASTM D790
Flexural Strength (Yield)	2400 psi	16.5 MPa	ASTM D790

**Hardness**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	55	55	ASTM D2240

**Thermal**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	220 °F	104 °C	ASTM D1525

Technical Data Sheet

# Ferro Pp NPP00NP01NA

Polypropylene  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

**Notes**

These are typical property values not to be construed as specification limits.