

Technical Data Sheet

Ferro Pp RPP30GT13UL NATURAL

Polypropylene
LyondellBasell Industries
Engineering Plastics

General	
Features	• Flame Retardant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.45	1.45 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	8.5 g/10 min	8.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	6500 psi	44.8 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	4.0 %	4.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	751000 psi	5180 MPa	
Tangent : 73°F (23°C)	760000 psi	5240 MPa	
Flexural Strength (73°F (23°C))	10000 psi	68.9 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	2.5 ft·lb/in	130 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	8.0 ft·lb/in	430 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	7.00 in·lb	0.791 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	300 °F	149 °C	
264 Psi (1.8 Mpa), Unannealed	270 °F	132 °C	
RTI Elec (0.06 In (1.6 Mm))	230 °F	110 °C	UL 746B
RTI Imp (0.06 In (1.6 Mm))	230 °F	110 °C	UL 746B
RTI Str (0.06 In (1.6 Mm))	230 °F	110 °C	UL 746B

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Arc Resistance	137 sec	137 sec	ASTM D495
Comparative Tracking Index (CTI)	600 V	600 V	UL 746A
High Voltage Arc Tracking Rate (HVTR)	0.00 in/min	0.00 mm/min	UL 746A
Hot-wire Ignition (HWI)	100 sec	100 sec	UL 746A

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.6 Mm))	V-0	V-0	UL 94

Additional Information

The value listed as Comparative Tracking Index was tested in accordance with ASTM D3638.

Technical Data Sheet

Ferro Pp RPP30GT13UL NATURAL

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.