

Technical Data Sheet

Gapex FPP30GQ16GN

Polypropylene
LyondellBasell Industries
Engineering Plastics

General	
Filler / Reinforcement	• Glass\Mineral, 30% Filler by Weight
Additive	• Impact Modifier
Features	• Chemically Coupled • Impact Modified
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.16	1.16 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	11 g/10 min	11 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	5100 psi	35.2 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	3.0 %	3.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	38000 psi	262 MPa	
Tangent : 73°F (23°C)	426000 psi	2940 MPa	
Flexural Strength (Yield, 73°F (23°C))	8300 psi	57.2 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.70 ft·lb/in	37 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	3.8 ft·lb/in	200 J/m	ASTM D4812
Gardner Impact	3.50 in·lb	0.395 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	290 °F	143 °C	
264 Psi (1.8 Mpa), Unannealed	215 °F	102 °C	

Additional Information
Filler Content, ASTM D2584: 32%

Notes

These are typical property values not to be construed as specification limits.