



## Technical Data Sheet

# Gapex RPP20EC12BK

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

### Product Description

Please contact A. Schulman for additional information.

### General

Uses	• Automotive Applications	
Automotive Specifications	• FORD WSK-M4D731-A2	• GM GMP.PP.004 Color: Black
Forms	• Pellets	

Technical Data Sheet

# Gapex RPP20EC12BK

Polypropylene  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	430 to 460 °F	221 to 238 °C
Middle Temperature	440 to 470 °F	227 to 243 °C
Front Temperature	450 to 500 °F	232 to 260 °C
Nozzle Temperature	450 to 500 °F	232 to 260 °C
Processing (Melt) Temp	430 to 460 °F	221 to 238 °C
Mold Temperature	100 to 150 °F	38 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Cushion	0.200 to 0.500 in	5.08 to 12.7 mm

**Notes**

These are typical property values not to be construed as specification limits.