

Technical Data Sheet

# Gapex RPP30DA

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

General	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.13	1.13 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	2.0 g/10 min	2.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	7300 psi	50.3 MPa	ASTM D638
Tensile Elongation (Break)	3.0 %	3.0 %	ASTM D638
Flexural Modulus	700000 psi	4830 MPa	ASTM D790
Flexural Strength (Yield)	11000 psi	75.8 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	1.1 ft·lb/in	59 J/m	
Unnotched Izod Impact			ASTM D4812
73°F (23°C), 0.125 In (3.18 Mm)	3.0 ft·lb/in	160 J/m	
Gardner Impact	3.00 in·lb	0.339 J	ASTM D3029

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	80	80	ASTM D2240

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	295 °F	146 °C	
264 Psi (1.8 Mpa), Unannealed	280 °F	138 °C	

Technical Data Sheet

# Gapex RPP30DA

Polypropylene  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	430 to 460 °F	221 to 238 °C
Middle Temperature	440 to 470 °F	227 to 243 °C
Front Temperature	450 to 500 °F	232 to 260 °C
Nozzle Temperature	450 to 500 °F	232 to 260 °C
Processing (Melt) Temp	430 to 460 °F	221 to 238 °C
Mold Temperature	100 to 150 °F	38 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Cushion	0.200 to 0.500 in	5.08 to 12.7 mm

## Notes

These are typical property values not to be construed as specification limits.