

Technical Data Sheet

# Gapex RPP45EA93GY

Polypropylene  
LyondellBasell Industries  
Engineering Plastics

**General**

- |                        |                                     |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 45% Filler by Weight |
| Forms                  | • Pellets                           |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.26	1.26 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	12300 psi	84.8 MPa	ASTM D638
Tensile Elongation (Break)	4.0 %	4.0 %	ASTM D638
Flexural Modulus	1.20E+6 psi	8270 MPa	ASTM D790
Flexural Strength (Yield)	21000 psi	145 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.5 ft·lb/in	81 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	8.3 ft·lb/in	440 J/m	ASTM D4812
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	82	82	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	320 °F	160 °C	
264 Psi (1.8 Mpa), Unannealed	305 °F	152 °C	

**Notes**

These are typical property values not to be construed as specification limits.