

Technical Data Sheet

Hifax BC 72G T/1 2078 (YZ9A)



Polypropylene Compounds

Product Description

Hifax BC 72G T/1 2078 is a talc filled PP copolymer, with good flowability, high stiffness, medium impact resistance and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 2078 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Stiffness; Good UV Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	1.00	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus	1900	MPa	ISO 178
Tensile Stress at Yield	22	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	8	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	108	°C	ISO 75B-1, -2