

Technical Data Sheet

Hifax CA 1110 G2 HF C11306



Polypropylene Compounds

Product Description

Hifax CA 1110 G2 HF C11306 is a 12% talc filled PP copolymer, with high melt flow, good impact resistance and very good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C11306 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Automotive Parts; Bumpers; Exterior Trim
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	0.98	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1300	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	16	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (-30 °C)	4.9	kJ/m ²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	111	°C	ISO 306