

## Technical Data Sheet

### Hifax ETA3041 YGYA BLK



Polypropylene Compounds

#### Product Description

Hifax ETA3041 YGYA BLK medium melt flow, 170 MPa flexural modulus, thermoplastic elastomeric olefin (TEO) resin has a good balance of flexibility and durability. It is typically used for a wide variety of molded-in color automotive exterior components.

<b>Application</b>	Automotive Parts
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	10	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	170	MPa	ISO 178
Tensile Stress at Yield	7	MPa	ISO 527-1, -2
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			