



## Hifax HSBMCB1158ACLS/3

### Compounded Polyolefin

#### Product Description

Hifax HSBMCB1158ACLS/3 high melt flow, 1,200 MPa flexural modulus, mineral filled thermoplastic elastomeric olefin (TEO) resin has a unique balance of flow, rigidity, and paintability. It was designed primarily for thin-walled bumper fascia applications.

#### Product Characteristics

<b>Test Method used</b>	ISO
<b>Processing Methods</b>	Injection Molding
<b>Features</b>	Good Dimensional Stability, Good Flow, High Impact Resistance , Low Temperature Impact Resistance, Good Moldability , Paintable, Good Stiffness
<b>Typical Customer Applications</b>	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density	ISO 1183	0.98	g/cm <sup>3</sup>
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	20	g/10 min
<i>Note: Alternative test method is ASTM D 1238-01.</i>			
<b>Mechanical</b>			
Tensile Stress at Yield	ISO 527-1, -2	18	MPa
Tensile Strain at Yield	ISO 527-1, -2	10	%
Flexural modulus	ISO 178	1200	MPa
<b>Thermal</b>			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	85	°C
<b>Additional Information</b>			
Mold shrinkage	ISO 294-4		