



## Hifax TKC 243X BLACK

Compounded Polyolefin

IMDS Number: 19524188

### Product Description

Hifax TKC 243X BLACK is a 10% talc filled PP copolymer, with good impact/stiffness balance. Product is available in black color, pellet form. This grade is delivered in BLACK color version.

*This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.*

### Product Characteristics

#### Availability

#### Processing Method

Injection molding

#### Features

Good impact/stiffness balance.

#### Typical Customer Applications

Designed for automotive painted bumper.

### Typical Properties

	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	7	g/10 min
Density (23 °C)	ISO 1183-1/A	0.97	g/cm <sup>3</sup>
<b>Mechanical</b>			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	16	MPa
Tens. Strain at Break	ISO 527-1, -2	150	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1200	MPa
<b>Impact</b>			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	60	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	6	kJ/m <sup>2</sup>
<b>Thermal</b>			
Vicat Softening Temperature A (10 N)	ISO 306	130	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	90	°C